

EAST Search History

Ref #	Hits	Search Query	DBs	Default Operator	Plurals	Time Stamp
L5	227712	magnet\$4 with (encapsulat\$3 or mold or resin or cas\$3)	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/02/21 15:44
L6	30	magnet\$4 with (encapsulat\$3 with mold with resin)	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/02/21 16:11
L7	293	magnetiz\$3 near3 resin	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/02/21 16:12
L8	199	magnetiz\$3 near2 resin	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/02/21 16:14
L9	56	7 and sensor	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/02/21 16:23
L10	2	7 and (bias near2 magnet)	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/02/21 16:25
L11	11	7 and encapsulat\$3	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/02/21 16:26
L12	77	heat with resistant with resin with magnet\$3 with powder	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/02/21 16:26